# Technical-Data-Sheet

## SR1F

## Heat shrinkable thin wall tube

shrink ratio 2 : 1 without adhesive

Heat shrinkable thin wall tube. Application: Insulating, bundling, marking, corrosion protection, mechanical protection. Characteristics: Thin wall, without thermoplastic adhesive, inscribable, resistant to chemical agents, stabilized against UV rays, free from paint-wetting inhibiting substances, non-corrosive, infusible, high flexibility, superior electrical properties, high tensile strength, resistant to cold flow (thermally stable), self-extinguishing (except transparent).



### Product description

| | |
|---|---|
| Article name | SR1F 19.1-9.5 |
| Material number | 457339 |
| Characteristics | Thin wall |
| | Without adhesive |
| | Inscribable |
| | Resistant to chemical agents |
| | Stabilized against UV rays |
| | Non-corrosive |
| | Free from paint-wetting inhibiting substances |
| | Infusible |
| | High tensile strength |
| | Superior electrical properties |
| | High tensile strength |
| | Resistant to cold flow (thermally stable) |
| | High flexibility |
| | Self-extinguishing (except transparent) |
| Applications | Insulating |
| | Bundling |
| | Marking |
| | Corrosion protection |
| | Mechanical protection |
| Family notes | A standard spool may include sections which have been tied together. |
| | Other lengths available on request. |

## Technical data

| | |
|---|---|
| Test standards | UL E172094 |
| | MIL-I-23053/5 Class 1 |
| Materials | Cross-linked polyolefin |
| | Free of lead and cadmium |
| Selection Note | lengths |
| Length L | 1 m |
| Colours | white |
| Inner diameter before shrinking (inch) | 3/4" |
| Inner diameter before shrinking (mm) | 19.1 mm |
| Inner diameter after shrinking (mm) | 9.5 mm |
| Recovered wall thickness | 0.76 mm |
| Elongation at break | 350 % |
| Elongation at break (associated standard) | ASTM D 638 |
| Tensile strength at break | 13 MPa |
| Tensile strength at break (associated standard) | ASTM D 638 |
| Longitudinal shrinkage | +/- 10 % |
| Longitudinal shrinkage (associated standard) | ASTM D 2671 |
| Shrink ratio | 2 : 1 |
| Shrink ratio (associated standard) | IEC 811-1-1 |
| Operating temperature range min | -55 °C |
| Operating temperature range max | 135 °C |
| Operating temperature range (associated standard) | IEC 216 |
| Shrinkage temperature | > 90 °C |
| Burning behaviour | self-extinguishing |
| Burning behaviour (associated standard) | UL 224 |
| Flexibility at low temperatures | -55 °C |
| Flexibility at low temperatures (associated standard) | ASTM D 2671 |
| Specific volume resistivity | $10^{14}$ Ω cm |
| Specific volume resistivity (associated standard) | ASTM D 257 |
| Dielectric strength | 20 kV/mm |
| Dielectric strength (associated standard) | ASTM D 2671 |
| Corrosion | none |
| Corrosion (associated standard) | ASTM D 2671 |
| Resistance to fungus and decay | No growth |
| Resistance to fungus and decay (associated standard) | AMS-DTL-7444 |

## Logistics data

| | |
|---|---|
| Delivery scope | Thin wall heat shrinkable tube in lengths |
| Shelf life description | Unlimited shelf life |
| Country of origin | Poland |
| Customs tariff number | 39173200 |

| | | | | |
|---|---|---|---|---|
| EAN-UPC | 4010311201368 | | | |
| Base quantity | 1 | 10 | 10 | 200 |
| Base unit of measure | Piece | Piece | Piece | Piece |
| Alternate quantity | 1 | 1 | 1 | 1 |
| Alternative unit of measure | Piece | Case | Pack | Carton |
| Lenght | 1000 | 1050 | 1050 | 1100 |
| Width | 60 | 40 | 40 | 400 |
| Height | 4.5 | 65 | 65 | 150 |
| Dimension unit | Millimetres | Millimetres | Millimetres | Millimetres |
| Volume | 0.27 | 2.73 | 2.73 | 66 |
| Volume unit | Cubic decimetres | Cubic decimetres | Cubic decimetres | Cubic decimetres |
| Gross weight | 0.043 | 0.439 | 0.439 | 9.517 |
| Net weight | 0.043 | 0.43 | 0.43 | 8.6 |
| Weight unit | Kilogram | Kilogram | Kilogram | Kilogram |